

TEST REPORT

No.: XMIN2012012053CM

Date: Dec 15, 2020

Page: 1 of 3

CUSTOMER NAME: HYDROBLOK GRAND INTERNATIONAL, INC.

ADDRESS: 701 S CARSON ST, CARSON CITY NV 89701-5239, USA

Sample Name : HYDROBLOK TILE BACKER BOARD

Manufacturer : HYDROBLOK GRAND INTERNATIONAL, INC.
Buyer : HYDROBLOK GRAND INTERNATIONAL, INC.

Material and Mark : Extruded polystyrene foam

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No. : SHIN2012079290CM

Date of Receipt : Dec 04, 2020
Testing Start Date : Dec 04, 2020
Testing End Date : Dec 15, 2020

Test result(s) : For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to

the sample(s) tested)

Signed for SGS-CSTC Standards Technical Services Co., Ltd Xiamen Branch Testing Center

Civi Huang

Authorized signatory



Inless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printer, werleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic forest documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-en-Document.aspx attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is divised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a ransaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or peparance of this document is unlawfull and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the soults shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

No.31 Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765830 www.sgsgroup.com.cn 中国•福建•厦门•火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e sgs.china@sgs.com



TEST REPORT

No.: XMIN2012012053CM


Date: Dec 15, 2020

Page: 2 of 3

Summary of Results:

No.	Test Item	Test Method	Result
1	Thermal Conductivity and Thermal Resistance	ASTM C518-17	See Result

Original Sample Photo(s):





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions of Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions-and-Conditions-and-Co

No.31 Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgsgroup.com.cn 中国·福建·夏门·火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e sgs.china@sgs.com



TEST REPORT

No.: XMIN2012012053CM

Date: Dec 15, 2020

Page: 3 of 3

Test Item: Thermal Conductivity and Thermal Resistance

Test Method: ASTM C518-17

Test Condition:

Specimen: 300mm×300mm×12.1mm, 1pc

Density: about 233kg/m³
Mean temperature: 23°C

Temperature difference: 20 °C

Lab Environmental Condition: 23±2°C, 50±5%RH

Test Result:

Test Item	Test Result
Thermal Conductivity	0.037 W/(m·K)
Thermal Resistance	0.327 (m ² ·K)/W

Note: 1. The test result can not be compared with other results obtained from different test conditions, and should not be cited to the use condition directly.



Inless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printectiveries, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic forest documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx titles of the forest on contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a cransaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or ppearance of this document is unlawfull and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the soults shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

No.31 Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765830 www.sgsgroup.com.cn 中国•福建•厦门•火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e sgs.china@sgs.com