

## HYDROBLOK JOINT SEALANT - TECHNICAL PROPERTIES

	IMPERIAL	METRIC
Skin Time	30-40 Minutes	
Consistency	Non-Sag	
Elongation at Break	250%	
Tensile Strength	200 psi	
Lap Shear	250 psi	
Application Temperature	35° F to 110° F	0° C to 42° C
Service Temperature	-60° F to 225° F	-50° C to 107° C
Shelf Life	12 mo. in unopened containers at 75° F	
Other Characteristics:	Conforms to ASTM C920, Type S, Grade NS, Class 25, Use NT, M and A.	
LEED® Qualifications :	Indoor Environmental Quality/4.1 Low-Emitting Materials/Adhesives and Sealants: 1 point	

**HYDRO-BLOK** sealant provides excellent adhesion to a variety of substrates without the use of a primer. This exterior-grade advanced polymer is weather resistant and contains no solvents or isocyanates. It is paint-able\*, non-yellowing and non-fading with very low VOCs.

*\*Due to the variety of different paint chemistries available, it is recommended to test a small section for paint adhesion prior to proceeding with a project.*

*Updated January 2016*

### HYDROBLOK GRAND INTERNATIONAL INC.

605 Lambert Pointe Dr, Hazelwood, MO 63042 United States  
[www.hydroblok.com](http://www.hydroblok.com) [info@hydroblok.com](mailto:info@hydroblok.com) 1-844-588-9559 (Toll-Free)